

The high performance sandwich core

Divinycell HP has been developed to meet demands in high temperature systems, and low temperature prepreg systems. The unique IPN chemical structure, yields impressive mechanical performance to a low weight. Divinycell HP's elevated temperature performance also extends to its 'in service' life as it will retain a high percentage of its mechanical properties despite exposure to high ambient temperatures.

It offers high properties in all significant areas including mechanical performance, elongation to break, ductility, adhesion/peel strength, fracture toughness and dimensional stability. Other key features of Divinycell HP include excellent chemical resistance, low water absorption and good thermal/acoustic insulation

Product Characteristics

- High temperature resistance
- High strength and stiffness to weight ratio
- Low water absorption
- Superior damage tolerance
- Fast and easy to process
- Good chemical resistance
- Acoustic and thermal insulation
- Consistent and homogenous material
- Low resin uptake

Mechanical properties Divinycell® HP - Imperial units

Property	Test Procedure	Unit		HP80	HP100	HP130	HP200	HP250
Compressive Strength ¹	ASTM D 1621	psi	Nominal	217	290	435	783	1,044
			Minimum	174	239	348	653	885
Compressive Modulus ¹	ASTM D 1621-B-73	psi	Nominal	15,225	19,575	24,650	44,965	58,015
			Minimum	13,050	16,675	21,025	38,435	50,763
Tensile Strength ¹	ASTM D 1623	psi	Nominal	406	508	696	1,030	1,334
			Minimum	319	362	508	914	1,160
Tensile Modulus ¹	ASTM D 1623	psi	Nominal	14,500	18,850	25,375	36,250	46,400
			Minimum	11,600	15,225	19,575	30,450	37,710
Shear Strength	ASTM C 273	psi	Nominal	181	232	319	508	653
			Minimum	145	203	276	464	566
Shear Modulus	ASTM C 273	psi	Nominal	4,060	5,075	7,250	10,590	14,070
			Minimum	3,190	4,060	5,800	9,427	11,748
Shear Strain	ASTM C 273	%	Nominal	38	40	40	45	45
Density	ISO 845	lb/ft ³	Nominal	5.0	6.3	8.1	12.5	15.6

All values measured at +73,4°F

1. Properties measured perpendicular to the plane

Nominal value is an average value of a mechanical property at a nominal density

Minimum value is a minimum guaranteed mechanical property a material has independently of density

Divinycell HP is type approved by:



Technical Characteristics

Technical Characteristics Divinycell® HP

Characteristics ¹	Unit	HP80	HP100	HP130	HP200	HP250	Test method
Density variation	%	± 10	± 10	± 10	± 10	± 10	-
Thermal conductivity ²	Btu x in/(ft ² x h x °F)	0.257	0.257	0.264	0.312	0.333	EN 12667
Coeff, linear heat expansion	x10 ⁻⁶ /°F	22.2	22.2	22.2	22.2	22.2	ISO 4897
Heat Distortion Temperature	°F	+257	+257	+257	+257	+257	DIN 53424
Continuous temp range	°F	-325 to +176	-325 to +176	-325 to +176	-325 to +176	-325 to +176	-
Max process temp	°F	+293	+293	+293	+293	+293	-
Dissipation factor	-	0.0005	0.0006	0.0009	0.0015	0.0019	ASTM D 2520
Dielectric constant	-	1.09	1.11	1.15	1.23	1.29	ASTM D 2520
Poissons ratio ³	-	0.4	0.4	0.4	0.4	0.4	ASTM 638

1. Typical values
2. Thermal conductivity at +50°F
3. Standard deviation is 0.045

Continuous operating temperature is typically -325°F to +176°F. The foam can be used in sandwich structures, for outdoor exposure, with external skin temperatures up to +212°F. For optimal design of applications used in high operating temperatures in combination with continuous load, please contact Diab Technical Services for detailed design instructions. Normally Divinycell HP can be processed at up to +293°F with minor dimensional changes.

Maximum processing temperature is dependent on time, pressure and process conditions. Therefore users are advised to contact Diab Technical Services to confirm that Divinycell HP is compatible with their particular processing parameters.

Physical characteristics

Format		Unit	HP80	HP100	HP130	HP200	HP250
Plain sheets	Length	inch	81.50	84.06	76.18	67.13	63.58
	Width	inch	40.16	41.14	37.20	32.48	30.51
GS sheet	Length	inch	40.55	42.01	38.07	33.54	-
	Width	inch	40.16	41.14	37.20	32.48	-

Disclaimer:

This data sheet may be subject to revision and changes due to development and changes of the material. The data is derived from tests and experience. If not stated as minimum values, the data is average data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect of the material or its use. The company reserves the right to release new data sheets in replacement.

All content in this publication is protected by international copyright laws. Copyright © Diab February 2016.

Issued: Feb 2016 Doc No: HP Feb 2016 rev21 IMP

Diab Group
 Box 201
 312 22 Laholm, Sweden
 Phone: +46 (0)430 163 00
 E-mail: info@se.diabgroup.com

